

TEST REPORT


Report Ref.	LEI19014647A Original		
Date Received	25/01/2019	Date Issued	29/01/2019

Company Name & Address	Fashion Formula Ltd Drakeglen House, 35-36 Disraeli Rd London, NW10 7AX GBR
Contact Name	Alexander Wills

Colour	Printed
Quality	Organic Cotton Drill
Supplier	Fashion Formula
Quoted Fibre Composition	100% Cotton
Retailer	General

Test	Method	Sample	Result
Free Formaldehyde	BS EN ISO 14184-1:2011	Beige Floral Woven Fabric	No Requirement

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.
Tests marked (*) in this report are not included in our UKAS scope of accreditation.



Stephen Dooney
(Laboratory Technician)

Free Formaldehyde BS EN ISO 14184-1:2011
Sample: Beige Floral Woven Fabric

Test	Method
Determination of Formaldehyde	BS EN ISO 14184-1:2011
Date Tested:	28/01/2019
Sample mass (g)	Formaldehyde (ppm)
2.5030	ND
2.5049	ND
Average Formaldehyde Concentration:	ND
Range of Calibration: 0.15 - 11.25 µg/ml	
The sample was received:	Unsealed
Comments: ND = Not Detected (<16ppm)	
Note: Spectrophotometer used for Colorimetric Determination	

Overall Test Result: No Requirement
Uncertainty: ±6%

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Any Pass/Fail statements do not take into account the Measurement of Uncertainty. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are close to Specification Limits / Requirements.