

## TEST REPORT


|                      |                       |                    |            |
|----------------------|-----------------------|--------------------|------------|
| <b>Report Ref.</b>   | LEI19014827A Original |                    |            |
| <b>Date Received</b> | 28/01/2019            | <b>Date Issued</b> | 07/02/2019 |

|                                   |  |
|-----------------------------------|--|
| <b>Company Name &amp; Address</b> | Fashion Formula Ltd<br>Drakeglen House, 35-36 Disraeli Rd<br>London, NW10 7AX<br>GBR |
| <b>Contact Name</b>               | Alexander Wills  |

|                                 |                           |
|---------------------------------|---------------------------|
| <b>Colour</b>                   | Printed                   |
| <b>Quality</b>                  | Organic, C Panama Natural |
| <b>Supplier</b>                 | Fashion Formula           |
| <b>Quoted Fibre Composition</b> | 100% Cotton               |
| <b>Retailer</b>                 | General                   |

| Test                             | Method                  | Sample | Result      |
|----------------------------------|-------------------------|--------|-------------|
| Colour Fastness to Light - STD 5 | BS EN ISO 105 B02: 2014 |        | See Results |
| Colour Fastness to Light - STD 5 | BS EN ISO 105 B02: 2014 |        | See Results |
| Colour Fastness to Light - STD 5 | BS EN ISO 105 B02: 2014 |        | See Results |
| Colour Fastness to Light - STD 5 | BS EN ISO 105 B02: 2014 |        | See Results |
| Colour Fastness to Light - STD 5 | BS EN ISO 105 B02: 2014 |        | See Results |

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.  
Tests marked (\*) in this report are not included in our UKAS scope of accreditation.



Heather Fletcher  
(Jobsheet Team Leader)

**Colour Fastness to Light - STD 5 BS EN ISO 105 B02: 2014**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

|   | Change in Shade Result | Performance Level |
|---|------------------------|-------------------|
| Blue  | 5+                     | B = 5             |
| Yellow  | 5+                     |                   |
|   |                        |                   |
| Overall performance level   | B                      |                   |
|   |                        |                   |
| BS 2543: 2004 Classification<br>(Minimum levels for customer reference) |                        |                   |
|   |                        |                   |
| Light Domestic  | B = 5                  |                   |
| General Domestic  | B = 5                  |                   |
| Heavy Domestic  | B = 5                  |                   |
| General Contract  | B = 5                  |                   |
| Severe Contract   | N/A                    |                   |

Overall Test Result: See Results  
Uncertainty: 1/2 grade

**Colour Fastness to Light - STD 5 BS EN ISO 105 B02: 2014**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

|   | Change in Shade Result | Performance Level |
|---|------------------------|-------------------|
| Orange  | 5+                     | B = 5             |
| Purple  | 5                      |                   |
| Pink  | 5+                     |                   |
|   |                        |                   |
| Overall performance level   | B                      |                   |
|   |                        |                   |
| BS 2543: 2004 Classification<br>(Minimum levels for customer reference) |                        |                   |
|   |                        |                   |
| Light Domestic  | B = 5                  |                   |
| General Domestic  | B = 5                  |                   |
| Heavy Domestic  | B = 5                  |                   |
| General Contract  | B = 5                  |                   |
| Severe Contract   | N/A                    |                   |

Overall Test Result: See Results  
Uncertainty: 1/2 grade

**Colour Fastness to Light - STD 5 BS EN ISO 105 B02: 2014**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

|   | Change in Shade Result | Performance Level |
|---|------------------------|-------------------|
| Med Green   | 5                      | B = 5             |
| Lilac   | 5                      |                   |
|   |                        |                   |
| Overall performance level   | B                      |                   |
|   |                        |                   |
| BS 2543: 2004 Classification<br>(Minimum levels for customer reference) |                        |                   |
|   |                        |                   |
| Light Domestic  | B = 5                  |                   |
| General Domestic  | B = 5                  |                   |
| Heavy Domestic  | B = 5                  |                   |
| General Contract  | B = 5                  |                   |
| Severe Contract   | N/A                    |                   |

Overall Test Result: See Results  
Uncertainty: 1/2 grade

**Colour Fastness to Light - STD 5 BS EN ISO 105 B02: 2014**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

|   | Change in Shade Result | Performance Level |
|---|------------------------|-------------------|
| Deep Red  | 5+                     | B = 5             |
| Black   | 5+                     |                   |
|   |                        |                   |
| Overall performance level   | B                      |                   |
|   |                        |                   |
| BS 2543: 2004 Classification<br>(Minimum levels for customer reference) |                        |                   |
|   |                        |                   |
| Light Domestic  | B = 5                  |                   |
| General Domestic  | B = 5                  |                   |
| Heavy Domestic  | B = 5                  |                   |
| General Contract  | B = 5                  |                   |
| Severe Contract   | N/A                    |                   |

Overall Test Result: See Results  
Uncertainty: 1/2 grade

**Colour Fastness to Light - STD 5 BS EN ISO 105 B02: 2014**  
**Conditioning Parameters: 20°C±2°C & 65% rH±4% rH**

|  | Change in Shade Result | Performance Level |
|--|------------------------|-------------------|
| Stone-Main   | 4                      | B = 5             |
| Dk Green   | 5+                     |                   |
|  |                        |                   |
| Overall performance level  | None met               |                   |
|  |                        |                   |
| BS 2543: 2004 Classification (Minimum levels for customer reference) |                        |                   |
|  |                        |                   |
| Light Domestic   | B = 5                  |                   |
| General Domestic   | B = 5                  |                   |
| Heavy Domestic   | B = 5                  |                   |
| General Contract   | B = 5                  |                   |
| Severe Contract  | N/A                    |                   |

Overall Test Result: See Results  
Uncertainty: 1/2 grade

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.*

*The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of  $k = 2$ , providing a level of confidence of approximately 95 %. Any Pass/Fail statements do not take into account the Measurement of Uncertainty. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are close to Specification Limits / Requirements.*