

EN71-3 TEST REPORT

Report Reference: LEI17103355

Date Received: 18/10/17

Date Tested: 19/10/17

Date Issued: 20/10/17

Submitted By: FASHION FORMULA
DRAKEGKEN HOUSE, 35-36 DISRAELI RD
LONDON
NW10 7AX

Contact Name: ALEX

Sample Details:

Description:	Stretch Jersey	Component(s) Tested:	See Below
Colour(s) :	Printed	Ref/ Style No:	Geo Elephant
Retailer:	None Given	End Use:	None Given
Fibre Composition:	None Given	No of Samples:	1
Supplier:	Fashion Formula		
Quality:	None Given		

Test	Method	Result
Migration of Certain Elements	BS EN 71-3:2013+A1:2014 Migration of Certain Elements in Accordance with REACH Regulation No. 1907/2006 on Registration, Evaluation, Authorisation and Restriction of Chemicals, Annex XVII. The European Council (EC) Directive 2012/7/EU – Cadmium amendment. Toy Safety Directive 2009/48/EC.	PASS

Results:

Category	Test	Result
III	Scraped off Material	Pass

Conclusion: The result of the test carried out meets the requirements of the standard.

EN71-3 TEST REPORT

Materials Sampled:

No.	DESCRIPTION	Weight (mg)	Test Solution Volume (mL)
	Textile		
1	Elephant Print Dec	305.1	15
2	Ivory Knitted Plain Fabric	306.9	15

Comments:

- The measurement of the ‘migration of certain elements’ was carried out using ICP-OES spectrometry.
- The following results relate to the concentration of soluble element.
- All sample solutions were adjusted to 1mol/L.

Results:

All Results and limits are quoted as mg/kg of named material.

Element	Al	Sb	As	Ba	B	Cd	Cr	Co	Cu	Pb	Mn	Hg	Ni	Se	Sr	Sn	Zn
EN71-3 Limit	70000	560	47	18750	15000	17	NA	130	7700	160	15000	94	930	460	56000	180000	46000
1	<100	<10	<10	<10	<10	<1	<0.12	<10	<10	<10	<10	<10	<10	<10	<10	<10	<10
2	<100	<10	<10	<10	<10	<1	<0.12	<10	<10	<10	<10	<10	<10	<10	<10	<10	<10


Element	Cr III	Cr VI	Organic Sn
EN71-3 Limit	460	0.2	12

Notes:

Migration of total Chromium has been determined as a first action. As the result is below the limit for Chromium VI (Cr VI), it can be inferred that the material complies with the requirements for both Chromium VI (Cr VI) and Chromium III (Cr III).

As the determination of the migration of Tin is below the limit for Organic Tin (12mg/kg), it can be inferred that the material complies with the requirement for Organic Tin.

This is in accordance with Annex I of the standard.

**EN71-3
TEST REPORT**Tel: +44 (0) 1942 265 700
Fax: +44 (0) 1942 670 788
www.intertek.com/consumergoods*N. Wilkinson***Approved:**

Natalie Wilkinson
(Specialist Team Leader)

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

LAB REPORT LEI17103355: PAGE 3 OF 3